

# PGJI2.MH25872

## Marking and Labeling Systems

No.	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use	Additional Conditions
Unprinted stock dsg: <b>Therman VIII</b>						
Inks: 4						
	Acrylic paint (smooth)	150	-40	X	X	-
	Alkyd paint (smooth)	150	-40	X	X	-
	Aluminum (smooth)	150	-40	X	X	O
	Epoxy paint (smooth)	150	-40	X	X	-
	Galvanized steel (smooth)	150	-40	X	X	-
	Glass (smooth)	150	-40	X	X	-
	Polyester paint (smooth)	150	-40	X	X	-
	Polyester powder paint (smooth)	150	-40	X	X	-
	Porcelain (smooth)	150	-40	X	X	-
	Stainless steel (smooth)	150	-40	X	X	-
	Epoxy powder paint (smooth)	125	-40	X	X	-
	Melamine (smooth)	100	-40	X	X	-
	Nylon - Polyamide (smooth)	100	-40	X	X	-
	Phenolic - Phenol Formaldehyde (smooth)	100	-40	X	X	-
	Polyurethane paint (smooth)	100	-40	X	X	-
	Polyurethane powder paint (smooth)	100	-40	X	X	-
	Unsaturated polyester - thermoset (smooth)	100	-40	X	X	-
	Acrylonitrile butadiene styrene (smooth)	80	-40	X	X	-
	Polybutylene terephthalate (smooth)	80	-40	X	X	-
	Polycarbonate (smooth)	80	-40	X	X	-
	Polyethylene (smooth)	80	-40	X	X	-
	Polyphenylene oxide/ether (smooth)	80	-40	X	X	-
	Polypropylene (smooth)	80	-	X	-	-
	Polystyrene (smooth)	80	-40	X	X	-
	Polyvinyl chloride (smooth)	80	-40	X	X	-