

# PGJI2.MH25872

## Marking and Labeling Systems

No.	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use	Additional Conditions
Unprinted stock dsg: <b>Therman X</b>						
Inks: 5						
	Acrylic paint	150	-40	X	X	O
	Alkyd paint	150	-40	X	X	O
	Aluminum	150	-40	X	X	O, G
	Chromate treated metal	150	-40	X	X	-
	Epoxy paint	150	-40	X	X	-
	Epoxy powder paint	150	-40	X	X	O
	Galvanized steel	150	-40	X	X	-
	Polyester paint	150	-40	X	X	-
	Polyester powder paint	150	-40	X	X	-
	Polyurethane paint	150	-40	X	X	-
	Porcelain	150	-40	X	X	-
	Stainless steel	150	-40	X	X	O, G
	Melamine	100	-40	X	X	-
	Nylon - Polyamide	100	-40	X	X	O, G
	Phenolic - Phenol Formaldehyde	100	-40	X	X	-
	Polycarbonate	100	-40	X	X	-
	Unsaturated polyester - thermoset	100	-40	X	X	O
	Acrylonitrile butadiene styrene	80	-40	X	X	O, G
	Epoxy	80	-40	X	X	-
	High density polyethylene	80	-40	X	X	O, G
	Polybutylene terephthalate	80	-40	X	X	O
	Polyethylene	80	-	X	-	-
	Polyethylene terephthalate	80	-40	X	X	-
	Polyphenylene oxide/ether	80	-40	X	X	-
	Polyphenylene sulfide	80	-40	X	X	-
	Polypropylene	80	-40	X	X	O
	Polystyrene	80	-40	X	X	O
	Polyvinyl chloride	80	-40	X	X	-
	Acrylic	60	-40	X	X	-