

## PGDQ2/PGDQ8 MH14014

### Marking and Labeling Systems – Component

<b>MIRVY IV</b>	Max Temp	Min Temp	Indoor Use	Outdoor Use	Additional Comments
Acrylic paint (AC PT)	212°F/100°C	-40°F/-40°C	X	X	-
Alkyd paint (AK PT)	212°F/100°C	-40°F/-40°C	X	X	-
Nylon - polyamide (PA)	212°F/100°C	-40°F/-40°C	X	X	-
Stainless steel (SS)	212°F/100°C	-40°F/-40°C	X	X	-
Aluminum (AL)	176°F/80°C	-40°F/-40°C	X	X	-
Epoxy powder paint (EP PDR PT)	176°F/80°C	-40°F/-40°C	X	-	-
Southern yellow pine	176°F/80°C	-	X	-	-
Unsaturated polyester - thermoset (UP)	176°F/80°C	-	X	-	-
Galvanized steel (GS)	140°F/60°C	-40°F/-40°C	X	X	-
Polyester paint (PER PT)	140°F/60°C	-40°F/-40°C	X	X	-
Acrylonitrile EPDM styrene (AES) plastic	104°F/40°C	-40°F/-40°C	X	X	-
Acrylonitrile butadiene styrene (ABS)	104°F/40°C	-40°F/-40°C	X	X	-
Polyethylene (PE)	104°F/40°C	-40°F/-40°C	X	X	-
Polyphenylene oxide/ether (PPOX)	104°F/40°C	-40°F/-40°C	X	X	-
Polypropylene (PP)	104°F/40°C	-40°F/-40°C	X	X	-
Polystyrene (PS)	104°F/40°C	-40°F/-40°C	X	X	-
<b>MIRVY IV (Type A)</b>					
Metals	212°F/100°C	-	X	X	-
Plastic Group I	212°F/100°C	-	X	X	-
Plastic Group II	176°F/80°C	-	X	X	-
Plastic Group V	176°F/80°C	-	X	X	-
Plastic Group VI	176°F/80°C	-	X	X	-
Plastic Group VIII	176°F/80°C	-	X	X	-
Acrylonitrile EPDM styrene (AES) plastic	104°F/40°C	-	X	X	-

G - Occasional exposure to Gasoline splashing.  
O - Occasional exposure to Lubricating Oil.